

HIPS/ABS – Regrind Mix

PRODUCT DESCRIPTION

A mixed regrind stream comprising ABS and HIPS with minor associated polymers recovered during processing. Supplied as a blended regrind rather than a single-polymer grade – the table below reflects typical batch composition.

Typical Properties and Characteristics

PROPERTY	VALUE / UNIT
ABS	47 %
HIPS	38 %
PP (filled)	7 %
TPE	3 %
HDPE (glass filled)	2 %
Polycarbonate	2 %
PA11	1 %

Source material: UK post-consumer / post-industrial mixed processing residue.

Composition reflects typical batch proportions and may vary. Contact us to discuss your specification.

Note: The nominal properties reported herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification purposes.